SHERWIN-WILLIAMS.

TECHNICAL DATA SHEET

PE/P/Q FTX GREEN RAL 6003 HR – Code: 16268

Date: February 2022

Indice : A

<u>GENERAL FEATURES :</u>	CURING CONDITIONS :
This thermosetting powder contains polyester resins cured with fit curing agents specially selected for their superior resistance to UV radiation and outdoor weathering.	For stoving of the PE/P/Q FTX products, the use of the following combinations of time and temperature is recommended :
The Syntha Pulvin PE/P/Q FTX were created for coating	-10-18 minutes at 200°C
aluminium components used in architecture and fulfill the	45.22
requirements :	-15-22 minutes at 190°C – Temperature of the support -20-30 minutes at 180°C
-Qualicoat class 1 –category 1 (license P-0737). -GSB Florida 1 Year Quality (license 280 c).	TECHNOLOGICAL FEATURES AND RESISTANCE TESTS :
	Support used : aluminium panel ALQ-36
ADVISED CYCLES :	Film thickness : 60-80 microns
The surface to be coated must be cleaned from oils, grease or	Stoving : 10 minutes at 200°C
flash rust.	Frieheen europing test (ICO1E2O) . > E rem
A pretreatment Cr-free, Qualicoat or GSB approved, is required.	Erichsen cupping test (ISO1520) : >5 mm Reverse impact test (ISO6272-2; ASTM D 2794) : >2.5Nm
Provide the second s	Cylindrical bend test (ISO1519) : diameter 5 mm
HANDLING AND STORAGE :	
	Resistance to humidity (ISO6270-2) - 1000 hours :
Store at temperatures lower than 30°C; higher temperatures may	-no blistering
damage the powder by causing undesired alterations or blobs.	-indentation along the cross of maximum 1 mm.
Storage life in original package: 24 months	
TEOUNICAL DATA	NOTE TO USER :
TECHNICAL DATA :	
Specific gravity : 1.48 ± 0.05	The information contained in this document, while based on evidence and reliable methods cannot be considered
Theoretical spread rate (gr /m ²) - 70 μ m : 100-107	exhaustive.
Film thickness : 60 –80 microns	This information are current to the date of issuance of this data
Gloss level - 60° : (4 – 6) GU	sheet, therefore is under user's responsibility to verify that the
Particle size distribution :	data provided on this sheet are current to the date of the
-d(v,0.5) : (38.0-42.0) μm	product.
-fines content <12 μm : (86.0-96.0) %	The user, under its own responsibility, shall respect all the
	existing provisions on hygiene and safety and shall verify every
WAY OF APPLICATION :	time the features and the specific and appropriate way to use
	the product, cause the respect of the provisions is not under producer's direct control.
Apply with guns with negative terminal (60/80KV) or	The manufacturer does not guarantee nor assume any liability
triboelectric guns, automatically or manually.	or responsibility for whatsoever harm that might result from a
	misuse of the product or for damages that have arisen after the
	product's distribution.

INVER France – Groupe Sherwin Williams,

2 rue Jean Devaux - BP80088 - 79100 Thouars - France

T : +33 (0)5 49 96 05 00 - F : +33 (0)5 49 96 14 37