

Product	QD807082SM BS 18-B-25 GREY POLYESTER SEMI MATT
Curing	10 MINS @ 200C Metal Temperature
Brilliance	25-35
Approvals	Certificate Nos: P-0656, P-0676, P-1084, P-1097

Product tested and approved for the quality mark

Introduction

Sherwin-Williams' Powder Coatings' Class 1 'Qualicoat' approved range of Architectural Polyesters are recommended for use on aluminium exterior situations where the 'Qualicoat' specification applies. Inver Powder Coatings' attention to formulation and particle size control ensures optimum transfer efficiency, enabling applied costs to be better controlled.

Colour

Wide range of RAL colours available and specials manufactured to order

Gloss

Three levels available (all measured at an incident angle of 60°)

Category 1:	< 30 +/-5 units
Category 2:	31 – 70 +/- 7 units including "BR" Metallics
Category 3:	71 – 100 +/- 10 units

(Permissible variation from the nominal value)

Film Properties

Meets the following criteria:

Adhesion	ISO2409:1992 (2mm)	Gt 0
Indentation	ISO2815:1973	Min 80
Mandrel bend	ISO1519:1995 (5mm)	No cracking or detachment
Impact	ASTM D2794: 1969 (2.5Nm)	No cracking or detachment
Kesternich	ISO3231:1993 (0.21.S02-24 cycles)	Max 1mm corrosion creep from scribes
Acetic Acid Salt Spray	ISO9227:1990 (1000hrs)	Max 16mm ² over 10cm length of scribe
Machu	Qualicoat method B1 (j)	Max corrosion creep 0.5mm
Accelerated Weathering	ISO1 1341-1994 Luminous intensity 550 W/m ² (290-800Nm)	Loss of gloss max 50% of original value. Colour change as defined in Qualicoat table 2
Weathering	Florida 5° south facing 1 year (ISO2810:1974)	Residual gloss 50% of original (min)
Resistance to Mortar	ASTM B3260 (24hrs)	No residue after removal
Resistance to boiling water	2 hrs deionised water or 1 hr pressure cooker	No defects or detachment
Condensed water	DIN50017:1982 (1000 hrs) Max 1mm under film creep	No blistering
Solvent (xylene)	30 secs	Rating 3-4
Sawing, Milling, Drilling		No cracking or chipping
Cupping Test	ISO1 520: 1995 5 mm min	(typically 7-9 min)

Substrate used for these tests was aluminium alloy AA5005-H24 with a thickness of 0.8mm pre-treated according to DIN 50939: 1988

Qualicoat Approved Architectural Range

Fire Classification

A2-s1, d0 in accordance with EN 13501-1.
Classification reports available on request.

Specific Gravity

1.4 – 1.8 depending on colour, gloss etc

Coverage

9 – 12 sq. m/kg @ 50 microns (100% utilisation assumed) depending on colour and gloss

Film Thickness

Minimum 60 microns

Minimum Curing Conditions (Minutes at object temperature)

	Full Gloss Cat 3 & Semi Gloss Cat 2	Matt Cat 1
210°C	5 mins	8 mins
200°C	6 mins	10 mins
190°C	8 mins	13 mins
180°C	10 mins	Not recommended
170°C	13 mins	Not recommended

Maximum Cure Conditions

	Full Gloss Cat 3 & Semi Gloss Cat 2	Matt Cat 1
210°C	5-15 mins	8-15 mins
200°C	6-16 mins	10-20 mins
190°C	8-18 mins	13-23 mins
180°C	10-20 mins	Not recommended
170°C	13-23 mins	Not recommended

Storage

Store in dry, cool conditions, preferably below 30°C. Shelf life under these conditions will be approx 24 months.

Pre-treatment

Conversion coating is essential in all cases. A chromate or chromate-free pre-treatment approved by Qualicoat or GSB should be used prior to powder coating.

Application Guidelines

Sherwin-Williams' Powder Coatings 'Qualicoat' approved powder coatings are suitable for use with all known electrostatic powder spraying equipment designed for thermosetting powder application

Health & Safety

We recommend all users of powder coatings to refer to the Code of Safe Practice: Application of Powder Coatings by Electrostatic Spraying (published by the British Coatings Federation of Great Britain Ltd) and our appropriate Health & Safety Data Sheet.

Printed Date: Apr-24

QD807082SM - BS 18-B-25 GREY POLYESTER SEMI MATT

Attributes	
Chemical Type	Polyester
Specific Gravity (Theoretical) (kg/l)	1.66 +/-0.10
Coverage @ 60 µm DFT m ² /kg	9-12
Technical Features	
Film Properties	Range/Value
Recommended Film Thickness	60-80 microns
Flexibility (Cylindrical Mandrel)	
Flexibility (Conical Mandrel)	
Adhesion	
Gloss (60 degrees)	25-35
Gloss (20 degrees)	
Direct Impact (cm/kg)	
Reverse Impact (cm/kg)	
Erichsen Cupping Test (mm)	
Cure Cycle	10 MINS @ 200C Metal Temperature
Appearance	
Application	Suitable for automatic and manual electrostatic application. Please check with your sales representative for Tribo.
Pretreatment	The surface to be coated must be free from oils, grease, and flash rust. A good quality pre-treatment process is recommended for optimum performance.
Substrate	Suitable for metal substrate.
Approval	
Version	

The information on this sheet is based on experience or tests in the laboratory and is published in good faith in the belief that it will be of value. We can accept no responsibility for loss or damage, which may result from accident, misuse or operations not under our direct control.

Thoroughly review product label and Safety Data Sheet (SDS) for safety information and cautions prior to using this product.

Environmental Data Sheet (EDS), Product (SDS) please visit your local Sherwin-Williams facility or www.PaintDocs.Com. Please direct any questions or comments to your local Sherwin-Williams facility. **Note:** All purchases of products from Sherwin-Williams are exclusively subject to Sherwin-Williams' terms and conditions of sale which can be found at www.Sherwin.Com. Please review these terms and conditions prior to the purchase of the products. Sherwin-Williams warrants the product to be free of manufacturing defect in accordance with Sherwin-Williams' quality control procedures. Except for the preceding sentence, due to factors that are outside of Sherwin-Williams' control, including substrate selection, and customer handling, preparation, and application, Sherwin-Williams cannot make any other warranties related to the product or the performance of the product. **SHERWIN-WILLIAMS DISCLAIMS ALL WARRANTIES OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTY OF MERCHANTABILITY, THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE.** Liability for products proven to be defectively manufactured will be limited solely to replacement of the defective product or the refund of the purchase price paid for the defective product, as determined by Sherwin-Williams. Under no circumstances shall Sherwin-Williams be liable for indirect, special, incidental or consequential damages, lost profits or punitive damages arising from any cause whatsoever.

Internal Use-IU-COR-00047

SW-COMPANY USE-OTHER